

Received: 03/11/2009	Completed: 03/17/2009	Letter: J	rb	P.O.#:	Test Report #: 2-77638-0-
Client's Identification	Style: Normandy Lite. Content: 100% Polyester. Weight: 11 oz/yd ² . End Use: Banner, Sign & Billboard Media for UV, Solvent & Screen Printing.				
Tested For: Jaime L. Giannantonio Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Key Test: NFPA 701-2004 TM#2 Flat				235
	Tel: 1-(973)-627-8608		Ext: 124		
	Fax: 1-(973)-627-8506				

PC:1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2004 Edition - Test Method #2 - Flat Sheet Specimens

SPECIMEN CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially After 72 hours water leaching
 After 3 dry cleanings After 100 hours accelerated weathering
 After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	310
2	0	0	280
3	0	0	340
4	0	0	320
5	0	0	330
6	0	0	330
7	0	0	320
8	0	0	280
9	0	0	240
10	0	0	280

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 438 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 seconds	Exceeds 2.0 seconds	Exceeds 435 mm (17.1")

RETEST PROVISION: Test 5 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure Criteria, the item tested:

Passes; Fails; Requires testing of 5 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2004 Edition Test Method #2 Flat Sheet Specimens.

Heather E. Robertson

AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. /jb/mg

(Page 1 of 2)

MS. HEATHER ROBERTSON - MAR 31 2009

Received: 03/11/2009	Completed: 03/17/2009	Letter: J	rb	P.O.#:	Test Report #: 2-77638-0-
Client's Identification	Style: Normandy Lite. Content: 100% Polyester. Weight: 11 oz/yd ² . End Use: Banner, Sign & Billboard Media for UV, Solvent & Screen Printing.				
Tested For: Jaime L. Giannantonio	Key Test: NFPA 701-2004 TM#2 Flat			235	
Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Tel: 1-(973)-627-8608		Ext: 124		
	Fax: 1-(973)-627-8506				

PRECONDITIONING: 1 hr @ 220°F (Standard)
 24 hrs @ 68±9°F (Alternate: Material shrinks/distorts @ 220°F)

REMARKS:
None.

CONVERSION FACTORS:
 mm ÷ 25.4 = inches
 g/m² ÷ 28.35 x .835 = oz/yd²

(Page 2 of 2)