

Intertek  
UBC 26-7  
TEST RESULTS

**Client:** Ultraflex Systems Inc.  
**Project No.:** 3181043SAT-002B  
**Date:** 5/29/09

**SPECIMEN I.D.:** Ultravision Window Perf

***Classification Criteria***

Plastic materials that have a burning extent of 25 mm or less are classified as CC1.  
Plastic materials that have a burning rate of 64 mm/minute or less are classified as CC2.

Specimen	Total Time t (sec.)	Average Extent of Burning (mm)	Average Time of Burning t-30 (sec.)
1	31	1	1
2	31	2	1
3	31	1	1
4	31	1	1
5	31	2	1
6	31	1	1
7	31	1	1
8	31	1	1
9	31	1	1
10	31	1	1
<b>Average</b>	31	1	1

This material met the CC1 classification.